

Propane Tank Pad Product Information



Test Description	Result	Test Method
Water Absorption	< 1.0%	ASTM D2842
Compressive Strength @ 5% strain @ 23°C	670 kPa (97 psi)	ASTM D1621 & ASTM C165
Uniform load capacity of 24" x 24" pad	55000 lbs	-
Flexural Strength	550 kPa (80 psi)	ASTM C203
Tensile Strength	2280 kPa (330 psi)	ASTM D412
Dimensional Stability:		
Thermal & Humid Aging	< 1.0%	ASTM D2126 ASTM C1622 & ASTM C303
Density	120 kg/m ³ (7.5 pcf)	& ASTM D3575
Fungi Resistance	No fungal growth supported	ASTM G21